

Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

Amendment to the Claims:

This listing of claims replaces all prior versions, and listings, of claims in the application:

1. (Original) A transducer diaphragm, comprising:  
  
an IC-compatible support structure; and  
  
a polymeric membrane layer formed on the support structure.

2. (Original) The transducer diaphragm of claim 1,  
wherein:  
  
the polymeric membrane layer includes one of Mylar, FEP, a PTFE fluoropolymer, Teflon® AF, polyimide, a silicone, or Parylene.

3. (Original) The transducer diaphragm of claim 2,  
wherein:  
  
the polymeric membrane layer has a thickness in the range from about 0.1  $\mu\text{m}$  to about 10  $\mu\text{m}$ .

4. (Original) The transducer diaphragm of claim 1,  
wherein:  
  
the polymeric membrane layer is spun or deposited onto the support structure using micromachining techniques.

Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

5. (Original) The transducer diaphragm of claim 1,  
wherein:

the support structure is formed from an electrically  
insulating or semiconducting glass, ceramic, crystalline, or  
polycrystalline material.

6. (Original) The transducer diaphragm of claim 1,  
wherein:

the polymeric membrane layer adheres to the support  
structure without requiring gluing.

7. (Original) The transducer diaphragm of claim 1,  
further comprising:

an electret layer formed on the polymeric membrane layer by  
micro-machining techniques.

8. (Original) The transducer diaphragm of claim 7,  
wherein:

the electret layer is thermally annealed to stabilize  
charge therein.

9. (Original) The transducer diaphragm of claim 7,  
wherein:

Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

the electret layer is heated to about 100°C for about 3 hours for thermal annealing.

10. (Original) The transducer diaphragm of claim 7, wherein:

the electret layer comprises a charged dielectric film formed on the polymeric membrane layer.

11. (Original) The transducer diaphragm of claim 10, wherein:

the dielectric film is charged by implanting electrons into the dielectric film by means of a thyratron.

12. (Original) The transducer diaphragm of claim 10, wherein:

the dielectric film is formed from one of Mylar, FEP, a PTFE fluoropolymer, Teflon® AF, a silicone, or Parylene.

13. (Original) The transducer diaphragm of claim 7, wherein:

the electret has a saturated charged density from about  $2 \times 10^{-5}$  C/m<sup>2</sup> to about  $8 \times 10^{-4}$  C/m<sup>2</sup>.

Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

14. (Original) A transducer back plate, comprising:  
a support structure defining a back volume; and  
a membrane layer formed on the support structure, the  
membrane layer having a front face and a rear face, the membrane  
layer comprising a plurality of cavities extending from the  
front face to the rear face, thereby providing for communication  
between the front face and the back volume.

15. (Original) The transducer back plate of claim 14,  
further comprising:

a polymeric reinforcing film formed on the membrane layer,  
the plurality of cavities extending through the polymeric  
reinforcing film.

16. (Original) The transducer back plate of claim 15,  
wherein:

the polymeric reinforcing film includes one of Mylar, FEP,  
a PTFE fluoropolymer, Teflon® AF, a silicone, or Parylene.

17. (Original) The transducer back plate of claim 16,  
wherein:

Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

the polymeric reinforcing film has a thickness in the range  
from about 0.1  $\mu\text{m}$  to about 10  $\mu\text{m}$ .

18. (Original) The transducer back plate of claim 15,  
wherein:

the polymeric reinforcing film is spun or deposited onto  
the membrane layer using micromachining techniques.

19. (Original) The transducer back plate of claim 14,  
wherein:

the support structure is formed from an electrically  
insulating or semiconducting glass, ceramic, crystalline, or  
polycrystalline material.

20. (Original) The transducer back plate of claim 15,  
further comprising:

a spacer formed on the polymeric reinforcing film to define  
an air gap, the air gap communicating with the back volume  
through the plurality of cavities.

21. (Original) The transducer back plate of claim  
14, wherein:

Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

the plurality of cavities comprises an array of about 25,000 holes extending through the membrane layer.

22. (Original) The transducer back plate of claim 21, wherein:

the membrane layer has a diameter of about 8 millimeters.

23. (Original) The transducer back plate of claim 14, further comprising:

an electret layer formed on the membrane layer by micro-machining techniques.

24. (Currently amended) An electret sound transducer, comprising:

a transducer diaphragm including an IC-compatible membrane support structure and a polymeric membrane layer formed on the membrane support structure by micro-machining techniques, the transducer diaphragm having a first electrode;

a transducer back plate having a second electrode and formed by micro-machining techniques, the back plate membrane layer having a front face and a rear face, and having a plurality of cavities extending from the front face to the rear face and through said second electrodes, thereby providing for

Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

communication between the front face and a back volume behind  
the rear face; and

an electret layer formed on at least one of the transducer diaphragm or the transducer back plate, the transducer diaphragm being positioned adjacent to the transducer back plate to form an electret sound transducer.

25. (Original) The electret sound transducer of claim 24, wherein:

the polymeric membrane layer includes one of Mylar, FEP, a PTFE fluoropolymer, Teflon® AF, polyimide, a silicone, or Parylene.

26. (Original) The electret sound transducer of claim 25, wherein:

the polymeric membrane layer has a thickness in the range from about 0.1  $\mu\text{m}$  to about 10  $\mu\text{m}$ .

27. (Original) The electret sound transducer of claim 24, wherein:

the polymeric membrane layer is spun or deposited onto the membrane support structure using micromachining techniques.

Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

28. (Original) The electret sound transducer of claim 24,  
wherein:

the membrane support structure is formed from an  
electrically insulating or semiconducting glass, ceramic,  
crystalline, or polycrystalline material.

29. (Original) The electret sound transducer of claim 24,  
wherein:

the polymeric membrane layer adheres to the membrane  
support structure without requiring gluing.

30. (Currently amended) The electret sound transducer of  
claim 24, wherein:

the transducer back plate comprises a back plate support  
structure defining [a] said back volume and has a back plate  
membrane layer formed on the back plate support structure, ~~the~~  
~~back plate membrane layer having a front face and a rear face,~~  
~~the back plate membrane layer comprising a plurality of cavities~~  
~~extending from the front face to the rear face, thereby~~  
~~providing for communication between the front face and the back~~  
volume.



Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

31. (Original) The electret sound transducer of claim 30,  
further comprising:

a polymeric reinforcing film formed on the back plate  
membrane layer, the plurality of cavities extending through the  
polymeric reinforcing film.

32. (Original) The electret sound transducer of claim 31,  
wherein:

the polymeric reinforcing film includes one of Mylar, FEP,  
a PTFE fluoropolymer, Teflon® AF, a silicone, or Parylene.

33. (Original) The electret sound transducer of claim 32,  
wherein:

the polymeric reinforcing film is about 2.5 µm thick.

34. (Original) The electret sound transducer of claim 31,  
wherein:

the polymeric reinforcing film is spun or deposited onto  
the back plate membrane layer using micromachining techniques.

35. (Original) The electret sound transducer of claim 30,  
wherein:

Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

the back plate support structure is formed from an electrically insulating or semiconducting glass, ceramic, crystalline, or polycrystalline material.

36. (Original) The electret sound transducer of claim 31, further comprising:

at least one spacer positioned between the transducer diaphragm and the transducer back plate to define an air gap, the air gap communicating with the back volume through the plurality of cavities.

37. (Currently amended) The electret sound transducer of claim 36, wherein:

the plurality of cavities comprises an array of ~~about~~ at least 25,000 holes extending through the back plate membrane layer.

38. (Original) The electret sound transducer of claim 37, wherein:

the membrane layer has a diameter of about 8 millimeters.

39. (Original) The electret sound transducer of claim 38, wherein:

Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

the air gap is about 4.5  $\mu\text{m}$  deep.

40. (Currently amended) An electret sound transducer, comprising:

a transducer diaphragm including a membrane support structure and a membrane layer formed on the membrane support structure by micro-machining techniques, the transducer diaphragm having a first electrode;

a transducer back plate having a second electrode and formed by micro-machining techniques, the transducer back plate comprising a back plate support structure defining a back volume and a back plate membrane layer formed on the back plate support structure, the back plate membrane layer having a front face and a rear face, the back plate membrane layer comprising a plurality of cavities extending from the front face to the rear face and through the second electrode, thereby providing for communication between the front face and the back volume; and

an electret layer formed on at least one of the transducer diaphragm or the transducer back plate, the transducer diaphragm being positioned adjacent to the transducer back plate to form an electret sound transducer.

Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

41. (Original) The electret sound transducer of claim 40,  
further comprising:

a polymeric reinforcing film formed on the back plate  
membrane layer, the plurality of cavities extending through the  
polymeric reinforcing film.

42. (Original) The electret sound transducer of claim 41,  
wherein:

the polymeric reinforcing film includes one of Mylar, FEP,  
a PTFE fluoropolymer, Teflon® AF, a silicone, or Parylene.

43. (Original) The electret sound transducer of claim 42,  
wherein:

the polymeric reinforcing film has a thickness in the range  
from about 0.1  $\mu\text{m}$  to about 10  $\mu\text{m}$ .

44. (Original) The electret sound transducer of claim 41,  
wherein:

the polymeric reinforcing film is spun or deposited onto  
the back plate membrane layer using micromachining techniques.

45. (Original) The electret sound transducer of claim 40,  
wherein:

Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

the back plate support structure is formed from an electrically insulating or semiconducting glass, ceramic, crystalline, or polycrystalline material.

46. (Original) The electret sound transducer of claim 41, further comprising:

at least one spacer positioned between the transducer diaphragm and the transducer back plate to define an air gap, the air gap communicating with the back volume through the plurality of cavities.

47. (Original) The electret sound transducer of claim 46, wherein:

the plurality of cavities comprises an array of ~~about~~ more than 25,000 holes extending through the back plate membrane layer.

48. (Original) The transducer back plate of claim 47, wherein:

the membrane layer has a diameter of about 8 millimeters.

49. (Original) The electret sound transducer of claim 48, wherein:

Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

the air gap is about 4.5  $\mu\text{m}$  deep.

50. (Original) The electret sound transducer of claim 40,  
wherein:

the transducer has an open circuit sensitivity greater than  
about 25 mV/Pa.

51. (Original) The electret sound transducer of claim 50,  
wherein:

the transducer has a noise level of less than about 30 dB  
SPL.

52. (Original) The electret sound transducer of claim 52,  
wherein:

the transducer has a total harmonic distortion of less than  
about 2% at 110 dB SPL at 650 Hz.

53. (Currently amended) An electret sound transducer,  
comprising:

a transducer diaphragm including an IC-compatible membrane  
support structure and a membrane layer formed on the membrane

Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

support structure by micro-machining techniques, the transducer diaphragm having a first electrode;

a transducer back plate having a second electrode and formed by micro-machining techniques having a front face and a rear face, the back plate membrane layer comprising a plurality of cavities extending from the front face to the rear face through said second electrode, thereby providing for communication between the front face and a back volume behind said rear face; and

an electret layer formed on at least one of the transducer diaphragm or the transducer back plate, the transducer diaphragm being positioned adjacent to the transducer back plate to form an electret sound transducer having an open-circuit sensitivity greater than about 25 mV/Pa, a noise level of less than about 30 dB SPL, and a total harmonic distortion of less than about 2% at 110 dB SPL at 650 Hz.

54. (Original) The electret sound transducer of claim 53, wherein:

the transducer has an open circuit sensitivity of greater than about 35 mV/Pa.

Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

55. (Original) A method of fabricating a transducer diaphragm, comprising:

providing an IC-compatible support structure;

forming a polymeric membrane layer on the support structure;

forming an electrode on the polymeric membrane layer; and

etching a portion of the support structure to form a transducer diaphragm.

56. (Original) The method of claim 55, wherein:

the polymeric membrane layer includes one of Mylar, FEP, a PTFE fluoropolymer, Teflon® AF, polyimide, a silicone, or Parylene.

57. (Original) The method of claim 55, wherein:

the polymeric membrane layer is spun on to a surface of the support structure.

58. (Original) The method of claim 55, wherein:

the polymeric membrane layer is deposited on a surface of the support structure.

59. (Original) The method of claim 55, wherein:



Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

the polymeric membrane layer adheres to the support structure without requiring gluing.

60. (Original) The method of claim 55, wherein:

the polymeric membrane layer is formed at about room temperature.

61. (Original) The method of claim 55, wherein:

the polymeric membrane layer is formed to a thickness in the range from about 0.1  $\mu\text{m}$  to about 10  $\mu\text{m}$ .

62. (Original) The method of claim 55, wherein:

the support structure is formed from an electrically insulating or semiconducting glass, ceramic, crystalline, or polycrystalline material.

63. (Original) The method of claim 55, wherein:

etching a portion of the support structure includes etching a silicon layer with bromine trifluoride.

64. (Original) The method of claim 55, further comprising:

forming an electret layer on the polymeric membrane layer.

Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

65. (Original) A method of fabricating a transducer back plate, comprising:

providing a support structure having a front face and a back face, the front face being coated with an insulating layer;

etching the back face of the support structure to form a support layer adjacent to the insulating layer;

forming a plurality of cavities through the insulating layer, the cavities extending into the support layer;

forming a polymeric reinforcing layer on the insulating layer;

forming an electrode on the polymeric reinforcing layer;  
and

etching the support layer to free a composite membrane, such that the cavities are in communication with a back volume formed in the support structure.

66. (Original) The method of claim 65, wherein:

the polymeric reinforcing layer includes one of Mylar, FEP, a PTFE fluoropolymer, Teflon® AF, polyimide, a silicone, or Parylene.

67. (Original) The method of claim 65, wherein:

Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

the polymeric reinforcing layer is formed at about room temperature.

68. (Original) The method of claim 65, wherein:  
the polymeric reinforcing layer is formed to a thickness in the range from about .1  $\mu\text{m}$  to about 10  $\mu\text{m}$ .

69. (Original) The method of claim 65, wherein:  
the support structure is formed from an electrically insulating or semiconducting glass, ceramic, crystalline, or polycrystalline material.

70. (Original) The method of claim 65, wherein:  
the support layer is etched with bromine trifluoride.

71. (Original) The method of claim 65, further comprising:  
forming at least one spacer on the polymeric reinforcing layer to define an air gap.

72. (Original) The method of claim 65, wherein:  
the plurality of cavities comprises an array of about 25,000 holes extending through the insulating layer.

Attorney Docket No. 06618-447001  
Serial No. 09/574,448  
Amendment dated August 2, 2004  
Reply to Office Action dated  
April 2, 2004

73. (Original) The method of claim 72, wherein:

the insulating layer has a diameter of about 8 millimeters.

74. (Original) The method of claim 65, further comprising:

forming an electret layer on the polymeric reinforcing  
layer.